



Product Category: 05 41 00 - Structural Framing

Product Name: 1200S162-97

Important Properties Notes:

- Calculated properties are based on AISI S100-12 with S2-10
 Supplement, North American Specification for Design of Cold-Formed
 Steel Structural Members.
- The centerline bend radius is based on inside corner radii shown in thickness chart.
- Effective properties incorporate the strength cold work of forming as applicable per AISI A7.2.
- Tabulated gross properties are based on fullsection of the studs, away from punchouts.
- · For deflection calculations, use the effective
- · Allowable moment includes cold-work of forming.
- For the steels that have both 33 and 50 ksi listing, if the design is based on 50 ksi, the 50 ksi steel needs to be

specified. (ex. 362S162-43 (50 ksi))

Project Information

Name: Address:

Contractor Information Name:

Name: Contact: Phone: Fax:

Architect Information

Name: Contact: Phone: Fax:


Distributor/Rep Information

Name: Contact: Phone: Email /Web:

Properties

1200S162-97 Properties

Finish:	G60
Web Depth	12" in
Flange Width	1 5/8 in
Design Thickness	0.1017 in
Thickness	97 mils or 12GA
Yield stress, Fy	50 ksi
Weight	5.362 lb/ft



1200S162-97 Section Properties

Gross Section Properties

Cross sectional area (A)	1.576 in2
Moment of inertia (Ix)	26.976 In4
Section Modulus (Sx)	4.496 in3
Radius of gyration (Rx)	4.138 in
Gross moment of inertia (ly)	0.332 in4
Gross Radius of gyration (Ry)	0.459 in

Effective Section Properties

Moment of inertia for deflection (lxe)	26.5 in4
Section modulus (Sxe)	4.091 in3
Allowable bending moment (Ma)	122.49 In-k
Allowable bending moment from	112.82 In-K
distortional buckling (Mad)	
Allowable strong axis shear away	8145 lb
from punch-out (Vag)	
Allowable strong axis shear at	7410 lb
punch out (Vanet)	

Torsional Properties

St. Venant torsion constant (J x 1000)	5.433 in4
Warping constant (Cw)	10.331 in6
Distance from shear center to neutral	-0.691 in
axis (Xo)	
Distance from shear center to	0.47 in
mid-plane (M)	
Radii of gyration (Ro)	4.22 in
Torsional flexural constant (Beta)	0.973
Unbraced Length (Lu)	29.5 in

1200S162-97 Page 1



Product Category: 05 41 00 - Structural Framing

Product Name: 1200S162-97

Limiting Heights Properties

Limiting Wall Heights - Curtain Wall 1-Span

Spacing	5psf			15psf			20psf			25psf		
(inches)	L/120	L/240	L/360	L/240	L/360	L/600	L/240	L/360	L/600	L/240	L/360	L/600
12												
16												
24												

Spacing	30psf			35psf			40psf			50psf		
(inches)	L/240	L/360	L/600									
12												
16												
24												

Additional Specification Information

Studs Unlimited is an SFIA member. Studs Unlimited acts in accordance with the product and quality standards required by the SFIA program.

Studs Unlimited meets or exceeds ASTM C955, A653, and A1003.

LEED Specification Information

Materials & Resources Credit 2: Construction Waste Management - Studs Unlimited Steel Framing Products are formed from steel and are 100% recyclable. (1 point)

Materials & Resources Credit 4: Recycled Content intends to increase demand for building products that incorporate recycled content materials, therefore reducing impacts resulting from extraction and processing of new virgin materials. As discussed and demonstrated below, North American steel building products contribute positively toward points under Credits 4.1 and 4.2. The following is required by LEED-NC Versions 2.2 and 2009:

Credit 4.1 (1 point) Use materials with recycled content such that the sum of post-consumer recycled content plus one-half of pre-consumer content constitutes at least 10%(based on cost) of the total value of the materials in the project.

Credit 4.2 (1 point) Use materials with recycled content such that the sum of post-consumer recycled content plus one-half of pre-consumer content constitutes at least 20% of the total value of the materials in the project.

Materials & Resources Credit 5: Regional Materials - Contact Studs Unlimited directly for information at bjpowell@studsunlimited.com.

Studs Unlimited is located in Oklahoma City, Oklahoma. (1 point)

1200S162-97 Page 2